

Enhanced Visible Light Photocatalytic Decolorization of Azo Dye using Magnetic PANI/CuFe₂O₄/ZnO

Mini Review

Abstract

In this study, novel magnetic hybrid of PANI/CuFe₂O₄/ZnO was synthesized by in situ oxidative polymerization of aniline in the presence of CuFe₂O₄ as magnetic component and ZnO as photoactive component. The prepared sample was characterized by using X-ray diffraction, Fourier transform infrared spectroscopy, field emission scanning electron microscopy and UV-vis spectroscopy. The catalytic activity of PANI/CuFe₂O₄/ZnO was investigated by degradation of methyl orange (MO) in aqueous solution under visible light. The results indicated that the as prepared PANI/CuFe₂O₄/ZnO show highly enhanced photocatalytic activity. Moreover, the PANI/CuFe₂O₄/ZnO can be easily separated from the aqueous solution by an external magnet and reused for several cycles.

Keywords: Polyaniline; Magnetic; visible light; Photocatalyst; ZnO

Volume 7 Issue 1 - 2018

Nahid Rasouli* and Somayea Abasian

Department of Chemistry, Payame Noor University, Iran

***Corresponding author:** Nahid Rasouli, Department of Chemistry, Payame Noor University, P.O. Box 19395-3697, Tehran, Iran, Tel: +0098-32608028; Email: n.rasouli55@yahoo.com; n.rasouli@pnu.ac.ir

Received: October 13, 2017 | **Published:** January 31, 2018

Introduction

Semiconductor research has demonstrated the main application in areas such as hydrogen production through photocatalytic water splitting [1], dye sensitized solar cells [2] and photocatalytic treatment of harmful organics from air and water [3]. Developing of efficient visible light responsive photocatalysts for environmental remediation has become the main area in photocatalysis research because of the usage of solar light [4]. For the actual applications, ZnO photocatalysts are usually not suitable due to the inconvenient and expensive separation [5], high photocorrosion [6], and low quantum efficiency resulted from its wide band gap ($E_g = 3.37$ eV) and the rapid recombination of photo-generated carriers [7]. In this regard, the modified ZnO-based photocatalysis with conducting polymers such as PANI can respond to visible light region effectively [8]. Moreover, ZnO-based photocatalysis coupled with conducting polymers are difficult to separate and recover from aqueous solution. In this regard, CuFe₂O₄ as the important magnetic materials have been utilized with photocatalysts and allowing easy separation of the photocatalysts from the liquid after the photocatalytic process [9].

Synthesis of PANI/ZnCrFeO₄/ZnO Photocatalyst

The PANI/ZnCrFeO₄/ZnO sample was prepared by in situ polymerization of aniline on the surface of the ZnCrFeO₄ and ZnO samples that reported previously. In this procedure, 10mL of 0.1M aniline, 10mL of 0.125 ammonium peroxydisulfate and 30mL of 0.1M nitric acid solutions were added to 0.25g of synthesized ZnCrFeO₄ and 0.1g of ZnO at room temperature. Then, the mixture was stirred during the polymerization of aniline, which was completed within 24 h. Finally, the prepared PANI/ZnCrFeO₄/ZnO was dried at 60°C.

Photocatalytic activity

The control experiments were performed under visible

light irradiation in the absence of the photocatalyst and in the presence of ZnO, CuFeO₄, PANI/CuFe₂O₄/ZnO and polyaniline as photocatalysts under visible light irradiation.

Mechanism of photocatalytic activity

The photogenerated electrons of PANI can transfer to the conduction band of ZnO and CuFe₂O₄, and the holes from the valence band of ZnO and CuFe₂O₄ can transfer to HOMO of PANI. The photogenerated electrons can be captured by dissolved O₂ to yield the O₂^{•-}, HOO• and •OH radicals and have been involved in the degradation of dye.

Conclusion

We provide a simple method to synthesize the magnetically recyclable PANI/CuFe₂O₄/ZnO photocatalyst by an in situ oxidative polymerization. The resulting sample show an enhanced photocatalytic activity for degradation of Methyl orange (MO). The photocatalytic decolorization percent of MO dye on the surface of the samples was determined about 45%, 5%, 98% and 55% for ZnO and CuFeO₄, PANI/CuFe₂O₄/ZnO and polyaniline samples, respectively. Also, PANI/CuFe₂O₄/ZnO sample can be reused three times with only gradual loss of activity.

Acknowledgement

The financial support of the research council of Payame Noor University of Isfahan is gratefully acknowledged.

Conflict of Interest

None.

References

- Zhong DK, Sun JW, Inumaru H, Gamelin DR (2009) Solar water oxidation by composite catalyst/ α -Fe₂O₃ photoanodes. *JACS* 131(17): 6086-6087.

- Gonzalez-Valls I, Lira-Cantu M (2009) Vertically-aligned nanostructures of ZnO for excitonic solar cells: a review. *Energy & Environmental Science* 2: 19-34.
- Kaneco S, Katsumata H, Suzuki T, Ohta K (2006) Titanium dioxide mediated photocatalytic degradation of dibutyl phthalate in aqueous solution—kinetics, mineralization and reaction mechanism. *Chemical Energy Journal* 125(1): 59-66.
- Feng J, Hu H, Yue PL (2004) Discoloration and mineralization of orange II using different heterogeneous catalysts containing Fe: a comparative study. *Environmental Science & Technology* 38(21): 5773-5778.
- Li Y, Wang K, Wu J, Gu L, Lu Z, et al. (2015) Synthesis of highly permeable Fe₂O₃/ZnO hollow spheres for printable photocatalysis. *RSC Advances* 5(107): 88277-88286.
- Han C, Yang MQ, Weng B, Xu YJ (2014) Improving the photocatalytic activity and anti-photocorrosion of semiconductor ZnO by coupling with versatile carbon. *Phys Chem Chem Phys* 16(32): 16891-16903.
- Tang D, Ye H, Du D, Liu S, Li M, et al. (2015) Fabrication of ZnO/graphene flake-like photocatalyst with enhanced photoreactivity. *Applied Surface Science* 358: 130-136.
- Eskizeybek V, Sarı F, Gülce H, Gülce A, Avcı A (2012) Preparation of the new polyaniline/ZnO nanocomposite and its photocatalytic activity for degradation of methylene blue and malachite green dyes under UV and natural sun lights irradiations. *Applied Catalysis B: Environmental* 119: 197-206.
- Sun SH, Zeng H, Robinson DB, Raoux S, Rice PM, et al. (2004) Mono disperse MFe₂O₄ (M = Fe, Co, Mn) nanoparticles. *J Am Chem Soc* 126(1): 273-279.