

Expert optimization and prediction of bead volume of mild steel butt welded joint

Abstract

The volume of weld bead deposit on a welded joint, has a lot to say about the integrity of the weldment during its service life. Residual stresses, cracks etc can be greatly initiated with large weld bead. In this study, central composite design matrix was employed using Design Expert 7.01 software. A total of 20 sets of experiments were produced, the weld specimen was mild steel plate measuring 60mm x 40mm x 10mm. TIG welding machine with 100% Argon Shielding Gas was used for this experiment and at the end of the experiment, an optimum weld bead volume of 1105.75mm³/s was obtained with a coefficient of determination (R^2) value of 0.9744 using response surface methodology (RSM) as the predictive modeling tool. This quantity of bead volume is expected to contain the adequate molten metal that is required to make the desired bead penetration at a minimum cost with appropriate weld quality and productivity.

Keywords: butt welded joints, bead volume, mild steel, shielding gas

Special Issue - 2018

Odoemelam C, Achebo JI, Etin Osa EC

Department of Production Engineering, University of Benin, Nigeria

Correspondence: Odoemelam C, Department of Production Engineering, University of Benin, Nigeria,

Email chwodoems@gmail.com

Received: October 16, 2018 | **Published:** December 31, 2018

Introduction

Tungsten Inert Gas (TIG) welding technique is a metal joining process that uses an arc with a non-consumable tungsten electrode on a work piece to create a permanent joint.^{1,2} An inert gas (argon, helium or a mixture of both) sustains the arc and protects the molten metal from atmospheric contamination. Filler materials might sometimes be used.^{3,4} Huang et al.⁵ and Farhad and Heidari⁶ described the TIG welding process as one of the most popular technologies for welding thin materials in manufacturing industries because it produces high quality welds. However, these authors compared TIG welding with the metal inert gas (MIG) welding process and stick weld and came to a conclusion that TIG welding has poor joint penetration when thick materials are welded in a single pass. In a research carried out by Vasudevan,⁷ Marya and Edward⁸ were of the opinion that activated TIG welding process was observed to typically increase the penetration capability by 200-300% and thereby reducing weld time and costs for manufacturers. Leconte et al.⁹ also applied activated TIG welding process and noted that it improves upon conventional GTAW, by increasing the single pass joining thickness from 6 to 10mm for stainless steel which was another breakthrough in time and cost reduction during weld operation, but ignoring the volume content of bead deposited might affect the quality of the welded joint. Venkatesan and Esme et al.,¹⁰ analyzed the sectional geometry of single-pass bead and the overlap of the adjacent beads to have critical effects on the dimensional accuracy and quality of metal parts. Therefore In order to find the parameter for optimization, weld bead profile study is needed

Materials and Methods

Materials

100 pieces of mild steel coupons, measuring 60mm x 40mm x10mm were used for the experiments, the experiment was performed 20 times using, 5 specimen for each run. Figure 1 shows the weld torch, Figure 2 shows the tig machine, Figure 3 shows the argon gas cylinder and regulator for varying the gas flow rate while Figure 4 shows the mild steel weld sample. The range of values of the process parameters was obtained from the open literature accessed and

each parameter has two levels which comprise the high and low as expressed in Table 1 below.



Figure 1 TIG welding torch.



Figure 2 TIG equipment.

Methods

The Central Composite Design matrix with 6 central points, 6 axial points and 8 factorial points was developed using the Design Expert 7.01 software, which produced 20 experimental runs. The input parameters and output parameters made-up the experimental matrix and the responses recorded from the weld samples were used as the data.



Figure 3 Shielding gas cylinder and regulator.



Figure 4 Weld samples.

Table I Welding parameters and their levels

Parameters	Unit	Symbol	Coded value	
			Low (-I)	High (+I)
Current	Amp	A	120	190
Gas flow rate	Lit/min	G	10	17
Voltage	Volt	V	20	27

Results and discussion

The optimization objective was to reduce the volume of weld metal deposit, the randomized design matrix comprising of three input variables (current, voltage and gas flow rate) and their ranges in real values is presented in Figure 5, the response variable of interest is circled in orange colour. The model summary which shows the factors and their lowest and highest values including the mean and standard deviation is presented as shown in Figure 6. Result of Figure 6 revealed that the model is of the quadratic type which requires the polynomial analysis order as depicted by a typical response surface design. The minimum value for volume of weld metal deposit was observed to be 1020.260mm³/s, maximum value of 1317.830mm³/s, mean value of 1191.888 and standard deviation of 83.228. Also indicated in circle analysis of the model standard error was employed to assess the suitability of response surface methodology using the quadratic model to maximize the electrode heat transfer coefficient, minimize the aspect ratio, minimize the volume of weld metal deposit and also minimize the rate of heat transfer from the heat source to the work piece. The computed standard errors for the selected responses are presented in Figure 7.

Std	Run	Type	Factor 1	Factor 2	Factor 3
			A:Current Amp	B:Voltage volt	C:Gas Flow Rate L/min
15	1	Center	155.00	23.50	13.50
16	2	Center	155.00	23.50	13.50
17	3	Center	155.00	23.50	13.50
18	4	Center	155.00	23.50	13.50
19	5	Center	155.00	23.50	13.50
20	6	Center	155.00	23.50	13.50
9	7	Axial	129.77	23.50	13.50
10	8	Axial	180.23	23.50	13.50
11	9	Axial	155.00	20.98	13.50
12	10	Axial	155.00	26.02	13.50
13	11	Axial	155.00	23.50	10.98
14	12	Axial	155.00	23.50	16.02
1	13	Fact	140.00	22.00	12.00
2	14	Fact	170.00	22.00	12.00
3	15	Fact	140.00	25.00	12.00
4	16	Fact	170.00	25.00	12.00
5	17	Fact	140.00	22.00	15.00
6	18	Fact	170.00	22.00	15.00
7	19	Fact	140.00	25.00	15.00
8	20	Fact	170.00	25.00	15.00

Figure 5 Central composite design matrix (ccd).

Std	Run	Type	Factor 1 A: Current Amp	Factor 2 B: Voltage volt	Factor 3 C: Gas Flow Rate L/min	Response 1 Aspect Ratio Nil	Response 2 Volume of Weld Metal Deposit mm³/s	Response 3 Electrode Heat Transfer Coefficient W/m²°C	Response 4 Rate of Heat Transfer J/s
15	1	Center	155.00	23.50	13.50	0.9511	1255.38	259.78	3264
16	2	Center	155.00	23.50	13.50	0.9513	1255.42	259.77	3266
17	3	Center	155.00	23.50	13.50	0.9512	1255.39	259.79	3267
18	4	Center	155.00	23.50	13.50	0.9511	1255.41	259.8	3265
19	5	Center	155.00	23.50	13.50	0.9512	1255.38	259.78	3264
20	6	Center	155.00	23.50	13.50	0.9513	1255.41	259.79	3266
9	7	Axial	129.77	23.50	13.50	0.5136	1037.78	272.49	2992
10	8	Axial	180.23	23.50	13.50	0.6842	1278.34	260.24	3400
11	9	Axial	155.00	20.98	13.50	0.6256	1251.3	222.82	2805
12	10	Axial	155.00	26.02	13.50	0.8312	1198.65	255.62	3128
13	11	Axial	155.00	23.50	10.98	0.9752	1125.94	248.23	2932.5
14	12	Axial	155.00	23.50	16.02	0.7704	1149.76	243.61	3187.5
1	13	Fact	140.00	22.00	12.00	0.709	1061.3	243.61	2618
2	14	Fact	170.00	22.00	12.00	0.8485	1200.99	266.71	3323.5
3	15	Fact	140.00	25.00	12.00	0.8147	1020.26	239.91	2856
4	16	Fact	170.00	25.00	12.00	0.7204	1317.83	248.23	3612.5
5	17	Fact	140.00	22.00	15.00	0.602	1176.44	215.89	2967
6	18	Fact	170.00	22.00	15.00	0.7633	1135.17	235.92	3012
7	19	Fact	140.00	25.00	15.00	0.606	1116.7	289.87	2975
8	20	Fact	170.00	25.00	15.00	0.6378	1234.9	273.61	3368

Figure 6 Design matrix showing the real values and the experimental values.

Design Summary										
Study Type		Response Surface			Runs		20			
Initial Design		Central Composite			Blocks		No Blocks			
Design Model Quadratic										
Factor	Name	Units	Type	Low Actual	High Actual	Low Coded	High Coded	Mean	Std. Dev.	
A	Current	Amp	Numeric	140.00	170.00	-1.000	1.000	155.000	12.395	
B	Voltage	volt	Numeric	22.00	25.00	-1.000	1.000	23.500	1.240	
C	Gas Flow Rate	L/min	Numeric	12.00	15.00	-1.000	1.000	13.500	1.240	
Response	Name	Units	Obs	Analysis	Minimum	Maximum	Mean	Std. Dev.	Ratio	
Y1	Aspect Ratio	Nil	20	Polynomial	0.514	0.975	0.790	0.144	1.899	
Y2	Volume of Weld	mm³/s	20	Polynomial	1020.260	1317.830	1191.888	83.228	1.292	
Y3	Electrode Heat Tran	W/m²°C	20	Polynomial	215.890	289.870	253.774	16.805	1.343	
Y4	Rate of Heat Tran	J/s	20	Polynomial	2618.000	3612.500	3138.450	232.055	1.380	

Figure 7 RSM Design summary for optimizing weld parameters.

To understand the influence of the individual design points on the model's predicted value, the model leverages were computed as presented in Figure 8. Leverage of a point varies from 0 to 1 and indicates how much an individual design point influences the model's predicted values. Leverages of 0.6698 and 0.6073 calculated for the factorial and axial points coupled with 0.1663 for the center point as

observed in Table 1 shows that the predicted values are very close to the experimental values. Hence lower residual value which shows the adequacy of the model. In assessing the strength of the quadratic model towards minimizing the volume of weld metal deposit one way analysis of variance (ANOVA) was done for each response variable and result is presented in Figure 9.




Figure 8 Result of computed standard errors.




Figure 9 Computed model leverages.

From the result of Figure 9 the Model F-value of 42.24 implies the model is significant. There is only a 0.01% chance that a "Model F-Value" this large could occur due to noise. Values of "Prob>F" less than 0.0500 indicate model terms are significant. In this case A, AB, AC, A², B², C² are significant model terms. Values greater than 0.1000 indicate the model terms are not significant. To validate the adequacy of the model based on its ability optimizes the volume of weld metal deposit. the goodness of fit statistics presented in Figure

10 were employed. Coefficient of determination (R-Squared) value of 0.9744 was obtained which shows the strength of response surface methodology and its ability to minimize the volume of weld metal deposit. Adjusted (R-Squared) value of 0.9513 was also observed in Figure 10 which indicates a model with 95.13% reliability. Adeq Precision measures the signal to noise ratio. A ratio greater than 4 is desirable.




Figure 10 ANOVA table for validating the model significance towards minimizing the volume of weld metal deposit.

To obtain the optimal solution, we first consider the coefficient statistics and the corresponding standard errors. The computed standard error measures the difference between the experimental terms and the corresponding predicted terms. Coefficient statistics for bead volume is presented in Figure 11. The optimal equation which shows the individual effects and combine interactions of the

selected input variables (Current, Voltage and Gas flow rate) against the measured responses (Volume of weld metal deposit), is presented based on the actual factors as shown in Figure 12. The diagnostics case statistics which shows the observed values of each responses variable (Volume of weld metal deposit,) against their predicted values is presented in Figure 13.






Figure 11 GOF statistics for validating model significance towards minimizing the volume of weld metal deposit.



Factor	Estimate	df	Standard	95% CI		VIF
				Low	High	
Intercept	1255.74	1	7.69	1238.62	1272.87	
A-Current	67.27	1	5.10	55.91	78.64	1.00
B-Voltage	1.99	1	5.10	-9.37	13.36	1.00
C-Gas Flow Rat	7.53	1	5.10	-3.83	18.90	1.00
AB	39.67	1	6.66	24.82	54.51	1.00
AC	-45.04	1	6.66	-59.89	-30.20	1.00
BC	-4.48	1	6.66	-19.32	10.37	1.00
A ²	-36.68	1	4.96	-47.74	-25.62	1.02
B ²	-13.02	1	4.96	-24.08	-1.96	1.02
C ²	-43.82	1	4.96	-54.88	-32.76	1.02

Figure 12 Coefficient estimates statistics for minimizing the weld bead volume.



$$\begin{aligned}
 \text{Volume of Weld Metal Deposit} = & -8597.59387 \\
 & +40.60979 * \text{Current} \\
 & +26.85213 * \text{Voltage} \\
 & +887.91872 * \text{Gas Flow Rate} \\
 & +1.76306 * \text{Current} * \text{Voltage} \\
 & -2.00183 * \text{Current} * \text{Gas Flow Rate} \\
 & -1.98944 * \text{Voltage} * \text{Gas Flow Rate} \\
 & -0.16301 * \text{Current}^2 \\
 & -5.78592 * \text{Voltage}^2 \\
 & -19.47629 * \text{Gas Flow Rate}^2
 \end{aligned}$$

Figure 13 Optimal equation in terms of actual factors for minimizing the weld bead volume.

To assess the accuracy of prediction and established the suitability of response surface methodology using the quadratic model, a reliability plot of the observed and predicted values of bead volume is presented in Figure 14. The high coefficient of determination ($r^2=0.9744$) as observed in Figure 10 was used to establish the suitability of response surface methodology in minimizing the volume of weld metal deposit on the work piece. To accept any model, its satisfactoriness must be checked by an appropriate statistical analysis. To diagnose the statistical properties of the model, the normal probability plot of residual for bead volume is presented in Figure 15. To study the effects of combine variables on each response (Volume of weld metal deposit, 3D surface plots presented in Figure 16).

Finally, numerical optimization was performed to ascertain the

desirability of the overall model. In the numerical optimization phase, we ask Design Expert to minimize the weld bead, also determining the optimum value of current, voltage and gas flow rate. The interphase of the numerical optimization is presented as shown in Figure 17. The numerical optimization produces about twenty two (22) optimal solutions which are presented as shown in Figure 18. From the results of Figure 19 it was observed that a current of 140.00 Amp, voltage of 25.00 volt and a gas flow rate of 15.00 L/min will produce a weld material with volume of weld metal deposit (1105.57mm³/s). This solution was selected by Design Expert as the optimal solution with a desirability value of 96.70%. The contour plots showing weld bead volume response variable against the optimized value of the input variable is presented in Figure 19.

Diagnostics Case Statistics										
Standard Order	Actual Value	Predicted Value	Residual	Leverage	Internally Studentized Residual	Externally Studentized Residual	Influence on Fitted Value	Cook's Distance	Run Order	
1	1061.30	1075.58	-14.28	0.670	-1.318	-1.376	-1.960	0.352	13	
2	1200.99	1220.87	-19.88	0.670	-1.836	-2.139	*-3.05	0.684	14	
3	1020.26	1009.18	11.08	0.670	1.023	1.026	1.461	0.212	15	
4	1317.83	1313.15	4.68	0.670	0.432	0.414	0.589	0.038	16	
5	1176.44	1189.68	-13.24	0.670	-1.223	-1.258	-1.791	0.303	17	
6	1135.17	1154.81	-19.64	0.670	-1.814	-2.100	*-2.99	0.667	18	
7	1116.70	1105.38	11.32	0.670	1.046	1.051	1.497	0.222	19	
8	1234.90	1229.18	5.72	0.670	0.528	0.508	0.723	0.057	20	
9	1037.78	1038.87	-1.09	0.607	-0.092	-0.087	-0.109	0.001	7	
10	1278.34	1265.15	13.19	0.607	1.117	1.133	1.409	0.193	8	
11	1251.30	1215.57	35.73	0.607	* 3.026	** 9.88	* 12.29	* 1.42	9	
12	1198.65	1222.28	-23.63	0.607	-2.001	-2.451	*-3.05	0.619	10	
13	1125.94	1119.13	6.81	0.607	0.577	0.557	0.692	0.051	11	
14	1149.76	1144.47	5.29	0.607	0.448	0.429	0.534	0.031	12	
15	1255.38	1255.74	-0.36	0.166	-0.021	-0.020	-0.009	0.000	1	
16	1255.42	1255.74	-0.32	0.166	-0.019	-0.018	-0.008	0.000	2	
17	1255.39	1255.74	-0.35	0.166	-0.021	-0.020	-0.009	0.000	3	
18	1255.41	1255.74	-0.33	0.166	-0.019	-0.018	-0.008	0.000	4	
19	1255.38	1255.74	-0.36	0.166	-0.021	-0.020	-0.009	0.000	5	
20	1255.41	1255.74	-0.33	0.166	-0.019	-0.018	-0.008	0.000	6	

Figure 14 Diagnostics case statistics report of observed and predicted volume of weld metal deposit.




Figure 15 Reliability plot of observed versus predicted weld bead volume.




Figure 16 Normal probability plot of studentized residuals for minimizing weld bead volume.




Figure 17 Effect of current and voltage on volume of weld metal deposit.




Figure 18 Interphase of numerical optimization model for optimizing the weld bead volume

Conclusion

In this study, the response surface methodology was used to optimize the weld bead volume of tungsten inert gas mild steel welds. To validate the adequacy of the model based on its ability to optimize the weld bead volume, the goodness of fit statistics presented in Figure 10 was employed. Coefficient of determination (R^2) values of 0.9744

as observed in Figure 10 for weld bead volume indicated the adequacy of the models. To assess the accuracy of the prediction and established the suitability of response surface methodology using the quadratic model, a reliability plot of the observed and predicted values of each response was obtained as presented in Figure 15. The 3D surface plot as observed in Figure 17 shows the relationship between the input variables (voltage, current and gas flow rate) and the response

variable (weld bead volume). Similarly, based on the optimal solution the expert system generated contour plots as observed in Figure

20 showing several predicted responses and their respective input variables, all within the boundaries of experimental design.




Figure 19 Optimal solutions of numerical optimization.




Figure 20 Predicting the weld bead volume using contour plot.

The quality of a weld is determined by the quality of the weld bead geometry and rate of heat transfer. The bead volume is a very important factor to consider in assessing the quality of weldment. Weld bead geometry is described by the bead width, bead depth and bead volume. This study has shown that current has very strong influence on the on bead volume and rate of heat transfer. The models developed possess a variance inflation factor of 1.0 and P- values <0.05 indicating that the models are significant, the models also possessed a high goodness of fit with R^2 (Coefficient of determination) values of 94% for aspect ratio, 97% for bead volume. Adequate precision value of 22.813 was observed for the Bead volume. The model produced numerical optimal solution of Current 140.0Amp, Voltage of 25Volt and a Gas flow rate of 15L/min will produce a welded material having a bead volume 1105.57mm³ at a desirability value of 96.7%.

Acknowledgments

None.

Conflict of interest

There is no conflict of interest in this work.

References

1. Ahmed KH, Abdul Lateef, Mohd Javed, et al. Influence of welding speed on tensile strength of welded joint in TIG welding process. *Int Journal of Applied Engg Research*. 2010;1(3):518–527.
2. Achebo JI. Complex Behavior of Forces Influencing Molten Weld Metal Flow based on Static Force Balance Theory. *International Conference on Solid State Devices and Materials Science*. 2012;25:317–324.
3. Balasubramanian M, Jayabalan V, Balasubramanian V. Effect of process parameters of pulsed current tungsten inert gas welding on weld pool geometry of titanium welds. *ACTA metallurgical sinica*. 2010;23(4):312–320.
4. Aghakhani M, Mehrdad E, Hayati E. Parametric Optimization of Gas Metal Arc Welding Process by Taguchi Method on Weld Dilution. *International Journal of Modelling and Optimization*. 2011;1(3):216–220.
5. Huang Yong, Fan Ding, Fan Qinghua. Study of mechanism of activating flux increasing weld penetration of AC A-TIG welding for aluminum alloy. *Frontiers of Mechanical Engineering in China*. 2007; 2(4):442–447.
6. Farhad Kolahan, Mehdi Heidari. A new approach for predicting and optimizing weld bead geometry in GMAW, *International Journal of Mechanical Systems Science and Engineering*. 2009;3(11):1391–1394.
7. Vasudevan M. Computational and experimental studies on arc welded austenitic stainless steels. *Indian Institute of Technology*. 2007.
8. Marya M, Edward GR, Liu S. An investigation on the effects of gases in GTA welding of a Wrought AZ80 magnesium alloy. *Welding Journal*. 2004;83(7):203s–212s.
9. Leconte S, Paillard P, Philippe Pierre, et al. Effect of oxide fluxes on activation mechanisms of tungsten inert gas process. *Science and Technology of Welding & Joining*. 2006;11(4):389–397.
10. Venkatesan MV, Murugan N. Role of FCA welding Process Parameters on Bead Profile, Angular and Bowing Distortion of Ferritic Stainless Steel Sheets. *Journal of Engineering Science and Technology*. 2014; 9(1):107–122.
11. Esme U, Bayramoglu M, Kazancoglu Y, et al. Optimization of weld bead geometry in TIG welding process using grey relation analysis and Taguchi method. *Materials and Technology*. 2009;43(3):143–149.